

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



- (72) WIETELMANN, ULRICH, DE
(72) LISCHKA, UWE, DE
(72) WEGNER, MARION, DE
(71) CHEMETALL GMBH, DE
(51) Int.Cl.⁷ C07F 5/04, H01M 10/36, H01G 9/022
(30) 1998/06/30 (198 29 030.6) DE
(54) **BISOXALATOBORATE DE LITHIUM, SA PREPARATION ET
SON UTILISATION COMME SEL CONDUCTEUR**
(54) **LITHIUM BISOXALATOBORATE, THE PRODUCTION
THEREOF AND ITS USE AS A CONDUCTING SALT**

(57) L'invention concerne un nouveau composé bisoxalatoborate de lithium, un procédé permettant de le préparer, sur la base d'un composé lithium, d'acide oxalique ou d'un oxalate et d'un composé bore. L'invention concerne également un autre procédé de préparation, sur la base d'un hybride de lithium et de bore et d'acide oxalique, ainsi que l'utilisation de bisoxalatoborate de lithium comme sel conducteur dans des batteries aux ions de lithium.

(57) The invention relates to the novel lithium bisoxalatoborate compound, and to a method for producing this compound, on the basis of a lithium compound, an oxalic acid or an oxalate, and a boron compound. The invention also relates to another production method on the basis of lithium boron hydride and oxalic acid, and to the use of lithium bisoxalatoborate as a conducting salt in lithium-ion batteries.





PCT
WELTORGANISATION FÜR GEISTIGES EIGENTUM
Internationales Büro
INTERNATIONALE ANMELDUNG VERÖFFENTLICHT NACH DEM VERTRAG ÜBER DIE
INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT)

<p>(51) Internationale Patentklassifikation ⁷ : C07F 5/04, H01G 9/022, H01M 10/36</p>	A1	<p>(11) Internationale Veröffentlichungsnummer: WO 00/00495</p> <p>(43) Internationales Veröffentlichungsdatum: 6. Januar 2000 (06.01.00)</p>
<p>(21) Internationales Aktenzeichen: PCT/EP99/03908</p> <p>(22) Internationales Anmeldedatum: 7. Juni 1999 (07.06.99)</p> <p>(30) Prioritätsdaten: 198 29 030.6 30. Juni 1998 (30.06.98) DE</p> <p>(71) Anmelder (für alle Bestimmungsstaaten ausser US): MET-ALLGESELLSCHAFT AKTIENGESELLSCHAFT [DE/DE]; Bockenheimer Landstrasse 73-77, D-60325 Frankfurt am Main (DE).</p> <p>(72) Erfinder; und (75) Erfinder/Anmelder (nur für US): WIETELMANN, Ulrich [DE/DE]; Rodheimer Strasse 19, D-61381 Friedrichsdorf (DE). LISCHKA, Uwe [DE/DE]; Günter-Vogt-Ring 79, D-60437 Frankfurt am Main (DE). WEGNER, Marion [DE/DE]; Jüngerheimer Strasse 20, D-60528 Frankfurt am Main (DE).</p> <p>(74) Gemeinsamer Vertreter: METALLGESELLSCHAFT AKTIENGESELLSCHAFT; Bockenheimer Landstrasse 73-77, D-60325 Frankfurt am Main (DE).</p>	<p>(81) Bestimmungsstaaten: CA JP, KR, US, europäisches Patent (AT, BE, CH, CY, DE DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Veröffentlicht <i>Mit internationalem Recherchenbericht.</i></p>	
<p>(54) Title: LITHIUM BISOXALATOBORATE, THE PRODUCTION THEREOF AND ITS USE AS A CONDUCTING SALT</p> <p>(54) Bezeichnung: LITHIUM-BISOXALATOBORAT, HERSTELLUNG UND VERWENDUNG ALS LEITSALZ</p> <p>(57) Abstract</p> <p>The invention relates to the novel lithium bisoxalato borate compound, and to a method for producing this compound, on the basis of a lithium compound, an oxalic acid or an oxalate, and a boron compound. The invention also relates to another production method on the basis of lithium boron hydride and oxalic acid, and to the use of lithium bisoxalato borate as a conducting salt in lithium-ion batteries.</p> <p>(57) Zusammenfassung</p> <p>Beschrieben werden die neue Verbindung Lithium-bisoxalato borat, ein Herstellungsverfahren für diese Verbindung, ausgehend von einer Lithiumverbindung, Oxalsäure oder einem Oxalat und einer Borverbindung, ein weiteres Herstellungsverfahren, ausgehend von Lithiumborhydrid und Oxalsäure, und die Verwendung von Lithium-bisoxalato borat als Leitsalz in Lithium-Ionenbatterien.</p>		

-1-

LITHIUM BISOXALATOBORATE, THE PRODUCTION THEREOF AND ITS
USE AS A CONDUCTING SALT

The subject matter of the invention is lithium-bisoxalatoborate, $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$, two methods for the production thereof, and the use of lithium-bisoxalatoborate as a conducting salt in lithium ion batteries.

10 At present, lithium hexafluorophosphate (LiPF_6) is used as a conducting salt in all commercial lithium ion batteries. This salt has the necessary prerequisites for use in high-energy cells, i.e. it is easily soluble in aprotic solvents, it leads to electrolytes having high conductivities, and it has a high level of electrochemical stability. Oxidative decomposition first occurs at potentials of $>$ approximately 4.5V. LiPF_6 , however, also has serious disadvantages, which are mainly to be attributed to its lack of thermal stability. In solution, a dissociation into LiF and PF_5 takes place, even if only slight, which can lead to a cationic polymerisation of the solvent caused by the Lewis acid PF_5 . Upon contact with moisture, caustic hydrofluoric acid is released, which, on the one hand makes handling more difficult, because of its toxicity and corrosiveness, and, on the other hand, can lead to the (partial) dissolution of the transition-metal oxides (for example LiMn_2O_4) used as cathode material. In this way, the cycle stability of the respective electrochemical energy store is affected.

20

30 With this background in mind, intensive efforts are being made with the aim of developing alternative conducting salts. As such, lithium salts with perfluorated organic radicals are being tested above all. In particular, lithium trifluoromethanesulphonate, lithium bis(trifluoromethanesulphonyl)imide and the lithium methides, the most

-2-

fundamental of which is lithium bis(trifluoromethane sulphonyl)methide, are to be mentioned. These salts also have disadvantages, which hitherto prevented their use in commercial lithium batteries. The first-
5 mentioned salt does not give the electrolytes produced with it a sufficiently high conductivity. The last-mentioned salts admittedly have a conductivity which is equal to that of LiPF_6 , but because of the costly production methods are not of interest commercially.
10 Additionally, the imide has a corrosive effect on aluminium sheets, which are used as current diverters in many battery systems. Apart from this, because of the high fluorine content of the compounds, under unfavourable conditions exothermal reactions with
15 lithium are to be feared.

Lithium organoborates were tested as a further class of compound for use as a conducting salt. However, their use in lithium ion batteries was not seriously taken into consideration because of the low
20 oxidation stability, the safety problems linked with the formation of triorganoboranes as well as their high price.

The lithium borate complex salts $[\text{R}^1\text{O})_2\text{B}(\text{OR}^2)_2]\text{Li}$ described in DE 19633027 A1 represent a substantial
25 step forward. In this connection, R^1 and R^2 are the same or different, R^1 and R^2 are, if appropriate, connected to each other by a single bond or a double bond, R^1 and R^2 may be, individually or jointly, an aromatic ring from the group phenyl, naphthyl,
30 anthracenyl or phenanthrenyl, which can be unsubstituted or substituted one to four times by A or Hal, Hal standing for fluorine or chlorine and A meaning alkyl with 1 to 8 C-atoms, which in turn can be halogenised one to four times.

35 A disadvantage of these compounds is, on the one hand, the stabilities of the non-fluorinated

-3-

derivatives which, although improved, are in no way sufficient for the 3V systems required. Thus, for example, the unsubstituted lithium-bis[2,2-benzenediolato(2-)-O,O'] borate(1-) decomposes when an anodic potential of 3.6 V is exceeded. This value lies clearly below that of the standard conducting salt LiPF_6 (approximately 4.5V). As a result of increasing fluorine substitution of the organic radical, the oxidation stability rises to a value of approximately 4V for the perfluorated compound. However, these values are still lower than in the case of the standard salt LiPF_6 . The stability of the borates which are described, however, increases further because of a top layer formation during cyclisation, so that for some compounds almost sufficient stabilities are achieved. The stable compounds, however, have high molar masses (for example 378 g/mol for the perfluorated catecholate compound). Also, the preliminary stages required for the synthesis are not commercially available, but instead have to be produced in a costly way. Finally, compounds with CF bonds represent a potential safety risk, because they are not thermodynamically stable with respect to metallic lithium.

The underlying object of the invention is therefore to eliminate the disadvantages of the prior art and to develop an electrochemically stable lithium compound which has a good solubility in the aprotic solvents used by the battery industry, and also a method for the production thereof.

The object is achieved by the lithium compound lithium-bisoxalatoborate, $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$, indicated in claim 1. The independent claims 2 and 11 indicate two different methods for the production of lithium-bisoxalatoborate, claims 3 to 10 and 12 to 13 develop the method further and claim 14 indicates a use of the compound lithium-bisoxalatoborate.

-4-

Surprisingly, although it does not have any fluorine substituents, lithium-bis(oxalatoborate) has an excellent oxidation resistance. Thus, solutions of this salt in a mixture of ethylene carbonate (EC) and 1,2-dimethoxyethane (DME) are stable up to a voltage of 4.6V.

Furthermore, the conductivities which can be achieved with the salt in accordance with the invention are note worthy. Thus, a 0.56 m solution in a 1:1 mixture of EC and DME has a conductivity of 10.3 mS/cm at room temperature. In the usual solvent mixture propylene carbonate (PC)/DME (1:1), the conductivity of lithium-bisoxalatoborate in the case of different concentrations was measured (Figure 1). It can be inferred from the measurement results that with concentrations of up to 15% by weight, conductivities of up to 14 mS/cm are achieved (see Figure 1). These values are at the same level as, or even above, the conductivities which can be achieved with LiPF_6 . Thus, for 1 m solutions of LiPF_6 in dimethyl carbonate (DMC)/EC, 11.0 mS/cm is achieved.

The molar mass of 193.8 g/mol is admittedly approximately 27% above that of the LiPF_6 , but clearly below that of the borates described in EP 19633027 A1. This is not problematic, however, because electrolytes with lithium-bis(oxalatoborate) are also sufficiently conductive at lower concentrations (for example approximately 0.5 mol/l).

The lithium-bis(oxalatoborate) is easily soluble in water and in many polar aprotic solvents. In tetrahydrofuran (THF), approximately 42% by weight dissolves at 50°C and approximately 30% by weight dissolves at 23°C. It has a solubility of at least 15% by weight in diethylene glycol dimethyl ether (diglyme) and mixtures of diglyme and carbonates.

According to thermogravimetry experiments,


-5-

lithium-bis(oxalatoborate) is fully stable at up to approximately 300°C.


The lithium-bis(oxalatoborate) in accordance with the invention can be produced by reacting a lithium compound, such as lithium hydroxide (anhydrous or the hydrate) or lithium carbonate or a lithium alkoxide, with oxalic acid or an oxalate and a boron compound, such as boron oxide or boric acid or a boric acid ester.

The reaction can be carried out in a solvent, but does not necessarily have to be.

Preferably, lithium hydroxide or lithium carbonate is reacted with a stoichiometric amount of oxalic acid and a stoichiometric amount of boric acid or boron oxide in water, for example:



The reaction of lithium oxalate with oxalic acid and boric acid or boron oxide in water is also preferred, for example:



The sequence in which the components are added does not play a significant role. Preferably, oxalic acid is placed in an aqueous solution and the calculated amount of lithium base is added, or lithium oxalate is mixed with the 3-fold molar amount of oxalic acid. Subsequently, the calculated amount of boric acid or boron oxide is added to this partially neutralised oxalic acid solution.

The reaction temperature lies in the range between 0 and 100°C.

After the end of dosing, the mixture is heated to 50 to 100°C for a time and the water is then distilled

-6-

off. When crystallisation begins, the pressure is slowly lowered. The final drying takes place whilst stirring, at approximately 50 to 150°C and at approximately 1 mbar.

5 A solid product is obtainable which is partially lumpy, granular or fine-crystalline solid depending on the drying unit which is selected.

10 In a variant of the production method in accordance with the invention, water is not necessarily added as the solvent. However, water forms as a reaction by-product in different amounts. According to this variant of the method, it is provided that the starting materials are suspended in an organic solvent and the water which is released during the formation
15 reaction is removed by azeotropic distillation. All solvents which cannot be mixed with water or which can be mixed therewith to a limited extent, which form a water/solvent azeotrope and have such a high volatility that a subsequent product drying is possible, are
20 suitable for this process. Depending on the temperature and stirring conditions selected, the reaction starts spontaneously or is initiated by the addition of small amounts of water. The reaction temperature of the exothermic reaction lies between 0
25 and 150°C. The reaction mixture is subsequently heated to boiling temperature, the water of crystallisation and reaction water being removed by azeotropic distillation. Aromatic substances, such as benzene, toluene, xylene and ethyl benzene, are particularly
30 suitable for the course of the reaction and the azeotropic dehydration. Thus, for example, when toluene is used, the calculated amount of water can be precipitated within a reaction of time of approximately 2 to 4 hours.


35 The product in accordance with the invention precipitates in fine-crystalline, free-flowing form,

-7-

completely anhydrous and with good purity. It is separated from the reaction solvent by filtration, washed with an aprotic solvent (for example toluene or comparatively volatile hydrocarbons, such as hexane or pentane) and dried in a vacuum and/or at comparatively high temperatures (50 to 150°C).

Ethers which cannot be mixed with water, such as 2-methyl tetrahydrofuran, for example, are also suitable to a limited extent. In ethereal solvents, however, the lithium-bisoxalatoborate is only formed in impure form, i.e. it subsequently has to be purified in a relatively costly way by fractional crystallisation.

According to a further embodiment of the method in accordance with the invention, the product in accordance with the invention can also be obtained starting from lithium alkoxides LiOR and boric acid esters B(OR)₃ (with R = methyl, ethyl). In order to do this, a lithium alkoxide is mixed with a boric acid ester, the corresponding lithium tetraalkoxy borate Li[B(OR)₄] presumably being formed. This reaction does not necessarily require a solvent, but can be carried out in the presence of a solvent. The reaction mixture is subsequently reacted with oxalic acid and the alcohol component which is released is removed by distillation. Ideally, those boric acid esters which release as much volatile alcohols as possible are taken for this variant, i.e. the methyl compound or ethyl compound:




R = methyl, ethyl

The alcohol itself (i.e. methanol or ethanol) or an aprotic solvent, such as acetonitrile, can be used as the solvent. In this variant of the method, the


-8-

reaction temperature amounts to 0 to 100°C, the range between approximately 20 and 70°C being most suitable. When acetonitrile is used, then, after distillation of the alcohol which is released at normal or reduced pressure, the product in accordance with the invention precipitates upon cooling, in the form of colourless crystals, which can be filtered off and cleaned by washing with acetonitrile or another volatile, aprotic solvent (for example hexane, pentane, diethyl ether).

In accordance with a further variant of the method, LiBO_2 as both lithium compound and boron compound can be reacted together with oxalic acid to form the desired product:



In accordance with a further production method in accordance with the invention, lithium-bis(oxalatoborate) can also be prepared in aprotic media directly in fully anhydrous form. In order to do this, lithium boro-hydride is reacted in a solvent in accordance with the following reaction equation with two equivalents of anhydrous oxalic acid:



The reaction is advantageously carried out in a solvent in which LiBH_4 has a certain solubility, for example in ethers such as tetrahydrofuran (THF). Particularly advantageously, those solvents which are commonly used by the battery industry for the production of electrolytes are also used. In particular, polyethers, such as 1,2-dimethoxyethane, are suitable. The reaction temperature is not of crucial importance. It is limited downwards by the viscosity, which rises as the temperature falls. On

-9-

the other hand, however, it should not rise too high, in order to avoid a reductive attack, possible in principle, of the hydride on the oxalic acid or lithium-bis(oxalatoborate). In general, the
5 temperature range between 20 and 50°C is most suitable. The course of the reaction can be followed simply by observing the formation of gas.

In the following examples, the subject-matter of the invention is explained in greater detail.
10

Example 1: Synthesis of $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$ from lithium hydroxide, oxalic acid and boric acid in water with subsequent total evaporation.

15 252.14 g (2.00 mol) oxalic acid dihydrate and 23.94 g (1.00 mol) calcined LiOH were dissolved in 1500 g distilled water. The temperature rose to approximately 30°C and a clear solution formed as a result of the heat of neutralisation. Within 15 minutes, a solution
20 of 61.83 g (1 mol) boric acid in 1300 g water was then added (no visible exothermy). The solution was then concentrated by distillation at normal pressure. Within approximately 3 hours, 2165 g water were distilled off. The bottom temperature thereby rose to
25 104.2°C; crystals precipitated out of the colourless solution. A further 450 g water were distilled off, and the remaining suspension (411 g) was placed in a porcelain cup and put in a vacuum shelf dryer for complete evaporation. After vacuum drying for 24 hours
30 at 100°C, 184.8 g (95% yield) of a colourless granulate were obtained.

-10-

Analysis:

	found		theory	
	%	mol, normalised to B = 1	%	mol, normalised to B = 1
Li	3.68	1.06	3.58	1
B	5.4	1.00	5.58	1
C ₂ O ₄	85.6	1.95	90.8	2

NMR data: $\delta^{11}\text{B}$ (THF/C₆D₆): 7.70 ppm $h_q = 28$ Hz
 $\delta^{13}\text{C}$ (THF/C₆D₆): 159.1 ppm

- Example 2: Synthesis of Li[(C₂O₄)₂B] from lithium carbonate, oxalic acid and boric acid in toluene with subsequent azeotropic water separation.
- 126.07g of oxalic acid dihydrate (1.00 mol) and 30.98g of (0.500 mol) 99.8% boric acid were suspended in 600 ml toluene in a 2 l four-necked flask with thermometer, Teflon-blade stirrer and water separator. After heating to 60°C, first of all approximately 5 g of Li₂CO₃ were added using a solids dosing bulb. Within half an hour, no significant formation of gas could be established. Thereupon, 3.63 g of H₂O were added with a syringe. The reaction now began immediately, with strong formation of gas (2 l in 5 minutes). Within 5 minutes, the remaining amount of Li₂CO₃ (in total 18.50 g \approx 0.250 mol) was added. 6.19 l of gas (\approx 251 mmol, 100%) were thereby formed. The reaction mixture was then heated to boiling point and refluxed for 4 hours. Already after 20 minutes, 57.3 g of water (\approx 81% of the theoretically expected amount) had precipitated. Because the solid was baking strongly, it was cooled briefly and the reaction mass was scraped off the flask wall with a spatula. After 4 hours of refluxing, no more water precipitated (in total 72.0 g \approx 101 % of the theoretically expected amount); the yellowish

-11-

suspension was cooled and filtered using a glass frit. The cream-coloured, fine-crystalline sediment was washed twice with hexane and first dried at room temperature to constant weight (97.4 g \approx 100.5 % of the theoretical yield). As result of vacuum drying for 4 hours at 90°C, 0.2 g of residual moisture was removed.

Analysis:

NMR data: $\delta^{11}\text{B}$ (THF/ C_6D_6): 7.70 ppm

10

Example 3: Synthesis of $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$ from lithium hydroxide, oxalic acid and boric acid in toluene with subsequent azeotropic water separation.

15

8.70 g (125 mmol) of B_2O_3 (dried at 300°C in a drying pistol) and 63.04 g of (500 mmol) oxalic acid dihydrate were suspended in 300 ml of toluene in a 500 ml four-necked flask with KPG stirrer, water separator and thermometer. With the addition of 10.3 g (250 mmol)

20

$\text{LiOH}\cdot\text{H}_2\text{O}$, the temperature rose spontaneously to 39°C. The azeotropic water separation began immediately after the boiling point was reached, and within 16 minutes delivered 30.2 g of water (\approx 96% of the theoretically expected amount). Because the reaction product stuck to the flask wall, it was twice cooled slightly and the product was scraped off with a spatula.

25

Yield: 49.9 g of beige powder \approx 103% of the theoretical yield.

30

Example 4: Synthesis of $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$ from lithium carbonate, oxalic acid and boric acid in 2-methyl tetrahydrofuran (2-MeTHF) with subsequent azeotropic water separation.

35

252.14 g of oxalic acid dihydrate (2.00 mol) and 61.83g

-12-

of boric acid (1.00 mol) were suspended in approximately 0.8 l of 2-MeTHF and heated to 40°C in the same apparatus as in Example 2. 36.95 g (0.50 mol) of Li_2CO_3 were then added in small amounts. To
 5 accelerate the reaction, 2 x 1.5 ml water was sprayed in. The formation of gas took place relatively evenly and produced approximately 255 mmol within one hour. Refluxing was carried out thereupon, for 13 hours. After 5 hours, the theoretically expected amount of gas
 10 had escaped; the solution was intensely yellow in colour and a total of 120.6 g of 2-MeTHF-saturated water precipitated in the water separator (\approx 114.2 g of pure water \approx 83% of the theoretically expected amount). After 14 hours' reaction time, the yellow suspension
 15 was cooled and filtered by way of a G3-frit.

Analysis of the filtrate:

Filtrate: 1221 g, intensely yellow

20 NMR data: $\delta^{11}\text{B}$ (2-MeTHF/THF): 20.4 ppm $J_{\text{B-H}} = 205 \text{ Hz}$ 24%
 7.66 ppm $J_{\text{B-C}}[(\text{C}_2\text{O}_4)_2\text{B}]$ 65%
 5.25 ppm $J_{\text{B-H}} = 12 \text{ Hz}$ 11%

The product was subsequently freed from the solvent and crystallised out of THF/diethyl ether.

25 Yield: 83.3 g \approx 43% of the theoretical yield

Analysis of the product: the crystallisate dissolved in THF now only shows the ^{11}B -NMR-signal at 7.7 ppm

30 Example 5: Synthesis of $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$ from lithium methoxide, oxalic acid and trimethyl borate in methanol.

35 4.97 g of (131 mmol) lithium methoxide were dissolved in 119 g of methanol, and at 30°C, within 10 minutes,

-13-

and there was mixing with a solution of 13.51 g of (130 mmol) trimethyl borate in 30 g of methanol. The internal temperature thereby rose to 37°C; the reaction solution was clear and colourless. 23.40 g (260 mmol) of anhydrous oxalic acid were added to this solution all at once. The reaction mixture thereupon briefly turned curd-like (approximately 10 seconds), in order then to turn into a slightly viscous, milky suspension. No exothermy could be established. The reaction mixture was boiled at reflux (66.6°C) for 45 minutes and, after cooling, was decanted from an extremely finely dispersed soft solid (the solid could not be separated with a G 3 glass frit). The total evaporation of the clear decanted solution on the rotation evaporator produced 23.71 g of a greasy solid. Taking into account the decantation loss, this corresponds to 25.4 g \pm 101% of the theoretical yield. In the rotation evaporator, small amounts of a colourless sublimate were observed, which did not produce a ^{11}B -NMR signal and dissolved in water with an acidic reaction, which points to oxalic acid. The soft drying residue was not completely soluble in THF. The THF-soluble portion, however, only showed a ^{11}B -NMR signal at 7.7 ppm, which comes from $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$. The residue was digested with the approximately 5-fold amount of THF, filtered and evaporated. During evaporation, a greasy product resulted, which became increasingly dark in colour. After separation of the solvent, a colourless solid began to sublime off.

30

Yield (partly oily): 16.8 g (\approx 67% raw product)

The raw product was subsequently cleaned by recrystallisation out from THF/diethyl ether.

35

Yield: 10.2 g \approx 40% of the theoretical yield.

-14-

Example 6: Synthesis of $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$ from LiBH_4 and oxalic acid in THF

5 68.06 g (0.756 mol) of oxalic acid, dried at 120°C for two hours, were dissolved in 120 g of THF and cooled to -5 °C in a 0.5 l double-casing reactor. A solution of 8.10 g of LiBH_4 (0.372 mol) in 49.2 g of THF was added to this solution within 70 minutes. 22.6 l of gas (0.93 mol \pm 63% of the theoretically expected amount) were thereby given off. It was then quickly heated to boiling point. Approximately a further 8 l of gas thereby escaped. After 45 minutes' boiling at reflux (66°C), it was cooled to 24°C, a sample was taken and 3.3 g of LiH were added. 2.81 l of gas (\pm 116 mmol) were given off. The suspension was filtered, with 15 300.3 g of clear filtrate precipitating. The filtrate was then evaporated on the rotation evaporator to constant weight. 47.6 g (66% of the theoretical yield) of a white powder were obtained, which for the purpose of purification still had to be recrystallised. 20

Analysis:

NMR data:

25 $\delta^{11}\text{B}$ (sample before LiH addition): 9.7 ppm (32%);
7.7 ppm (68%)
 $\delta^{11}\text{B}$ (filtrate before evaporation): 9.7 ppm (7%);
7.7 ppm (88%); 5.2 ppm (5%)

-15-

Claims

1. Lithium-bisoxalatoborate, $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$.
2. Method for producing lithium-bisoxalatoborate, $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$, characterised in that a lithium compound
5 is reacted with oxalic acid or an oxalate and with a boron compound.
3. Method according to claim 2, characterised in that the reaction is carried out in a solvent.
4. Method according to one of claims 2 to 3,
10 characterised in that the lithium compound is LiOH or $\text{LiOH}\cdot\text{H}_2\text{O}$ or Li_2CO_3 or lithium oxalate or LiOR (with $\text{R} =$ methyl, ethyl).
5. Method according to one of claims 2 to 4,
15 characterised in that the boron compound is boron oxide B_2O_3 or boric acid H_3BO_3 or a boric acid ester B(OR)_3 (with $\text{R} =$ methyl, ethyl).
6. Method according to one of claims 2 to 3,
characterised in that LiBO_2 is used as the lithium and boron compound.
7. Method according to one of claims 3 to 5,
20 characterised in that the solvent is water or an alcohol with 1 to 5 C atoms or an organic solvent which cannot be mixed with water or can be mixed therewith to a limited extent and which forms an azeotrope with
25 water.
8. Method according to one of claims 3 to 5 and 7, characterised in that lithium hydroxide or lithium carbonate or lithium oxalate is reacted with oxalic acid and boric acid or boron oxide in the ratio $\text{Li}^+:$
30 oxalate: $\text{B}^{3+} = 1:2:1$ and in the presence of water.
9. Method according to one of claims 3 to 5 and 7 to 8, characterised in that lithium hydroxide or lithium carbonate or lithium oxalate is reacted with oxalic acid and boric acid or boron oxide in the ratio
35 $\text{Li}^+:$ oxalate: $\text{B}^{3+} = 1:2:1$, an organic solvent which forms an azeotrope with water is added to the water-

-16-

containing reaction mixture and the water is removed azeotropically.

10. Method according to claim 9, characterised in that the organic solvent which forms an azeotrope with water is benzene, toluene, xylene or ethyl benzene.

11. Method for producing lithium-bisoxalatoborate, $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$, characterised in that LiBH_4 is reacted with oxalic acid in an aprotic solvent.

12. Method according to claim 11, characterised in that the aprotic solvent is an ether or a polyether.

13. Method according to claim 12, characterised in that the ether is tetrahydrofuran (THF) or the polyether is 1,2-dimethoxyethane.

14. Use of lithium-bisoxalatoborate, $\text{Li}[(\text{C}_2\text{O}_4)_2\text{B}]$, as a conducting salt in lithium batteries.

1/1

